



## PRODUCT INFORMATION AND DATA SHEET

No 15-100176

### VAKPAK-SV film for packaging

#### Description:

VAKPAK SV- is a co-extrusion PA/PE film. Designed for vacuum packaging.

#### Typical values:

Properties	Test method	Unit	Typical values
Thickness	"Lietpak"	micron	80±5%
Unit weight	-	g/m <sup>2</sup>	78.7
Yield	-	m <sup>2</sup> /kg	12.7
Heat sealing temperature	"Lietpak"	<sup>0</sup> C	150 - 170
O <sub>2</sub> permeability (23 <sup>0</sup> C – 75 % RH)	ASTM D-3985	cc/m <sup>2</sup> – 24 h-	~55

The property values showed above are based on statistical values and, therefore, should not be construed as product specifications.

Film complies with EU regulations for direct contact with foodstuffs. This applies only if packaging material is used properly.

The company which is packing the product is responsible for checking if film is suitable for proposed application. Suitable secondary packaging system to be used. Suitable film thickness selection is in full responsibility of customer.

The guaranteed time of storage of packaging material is 12 months since the date of manufacture, unless the transport packaging of the pallets is damaged or terms of transportation and storage are violated.

Products must be stored in premises with a roof which is protecting the product against direct sunlight, under 15-25°C temperature, 40-60 % relative humidity and at least 1m distance from heating appliances.

Traces of colour are allowed in film if they are not visible in single film sheet.

Dated 2015-05-27

Approved by R.S.

#### UAB „Lietpak“

A. Mickevicius str. 165  
Cekoniskes settlement  
LT-14207 Vilnius district  
Lithuania

Tel. (+370 5) 249 1000  
Fax. (+370 5) 249 0272

[www.lietpak.lt](http://www.lietpak.lt)  
[lietpak@lietpak.lt](mailto:lietpak@lietpak.lt)

IBAN: LT357300010000052194  
„Swedbank“, AB  
Bank code: 73000

Company code: 125261991  
VAT code: LT252619917