

PRODUCT INFORMATION AND DATA SHEET

No 17-511

VAKPAK-SV film for packaging

Description:

VAKPAK SV- is co-extrusion PA/PE film. Designed for vacuum atmosphere packaging.

Typical values:

Properties	Test method	Unit	Typical values
Thickness	"Lietpak"	micron	80±10%
Unit weight	"Lietpak"	g/m ²	78,5
Yield	"Lietpak"	m²/kg	12,7
Heat sealing temperature	"Lietpak"	0C	145 - 200
O ₂ permeability (23 ⁰ C – 75 % RH)	ASTM D-3985	$cc/m^2 - 24 h$	~50

The property values showed above are based on statistical values and, therefore, should not be construed as product specifications.

Film complies with EU regulations for direct contact with foodstuffs. This applies only if packaging material is used properly.

The company which is packing the product is responsible for checking if film is suitable for proposed application. Suitable secondary packaging system to be used .Suitable film thickness selection is in full responsibility of customer.

The guaranteed time of storage of packaging material is 12 months since the date of manufacture, unless the transport packaging of the pallets is damaged or terms of transportation and storage are violated.

Products must be stored in premises with a roof which is protecting the product against direct sunlight, under 15-25°C temperature, 40-60 % relative humidity and at least 1m distance from heating appliances.

Traces of color are allowed in film if they are not visible in single film sheet.

Technical changes reserved for enhancing the quality of product without prior information.

Dated 2017-04-05 Approved by R.S.

Bank code: 73000

Company code: 125261991

VAT code: LT252619917